

8/9/2024

North Slope Crushing
P.O. Box 908
Kamas Utah, 84036

Sieve Analysis - Standard

AASHTO: T-27, T-11

Project No 008220
Client Reference No
Barcode WVCL4352
Material Source Browns Pit
Material Description Bedding Sand
Project North Slope Crushing Lab Services - 8220
Location Detail

Date Tested 8/7/2024 12:00 PM
Sample Rec. Date 8/6/2024 12:00 PM
Date Sampled 8/6/2024 12:00 PM
Sampled By Client

Sieve Size	Indiv Wt. Retained	Indiv % Retained	Cumulative Percent Retained	Cumulative Percent Passing	Spec Min%	Spec Max%	Pass Fail
3/4"	0.0	0.0%	0.0	100			
1/2"	0.0	0.0%	0.0	100			
3/8"	2.5	0.5%	0.5	100			
#4	91.0	17.8%	18.3	82			
#10	104.7	20.5%	38.8	61			
#16	33.2	6.5%	45.3	55			
#40	46.4	9.1%	54.4	46			
#100	106.4	20.8%	75.2	25			
#200	62.4	12.2%	87.4	13			
Total=Pan	510.7	100.0%	0.9				
Dry Original Wt. 510.7				AASHTO: T-89, T-90			
Washed Wt. 455.6				Liquid Limit			
- No. 200 Washed Out 55.1				Plastic Limit			
- No.200 Sieved Out 8.8				Plasticity Index			
Total - No.200 63.9				= 12.5%			

Comments

Technician Anna Marsh
Digital Signature By User Login

Manager Belinda Torres
Title Laboratory Manager
Digital Signature By User Login

Test results relate only to the sample tested. This test report shall not be reproduced, except in full, without the prior written approval of CMT West Valley Main Office - (801)908-5859.

Lab Address 2688 S. Redwood Rd. Suite E,F,G,H West Valley City Utah, 84119

System Link <http://cmt-data.com/assignments/B39C20C2-B55E-4065-0FB3-9651DC63C917>

System Path North Slope Crushing Lab Services - 8220 / SOILS - FIELD AND LAB TESTING / 008220 SieveCustStd KK08/09/2024